



# PM600

## MILITARY GREASE

- GEAR OILS
- MOTOR OILS
- HYDRAULIC OILS
- PIPE COATINGS
- THREAD SEALANTS
- BEARING GREASES
- SPECIALTY GREASES
- THREAD COMPOUNDS
- SUCKER ROD COATINGS
- OUTSIDE PRESERVATIVES
- WIRELINE GREASE SEALS
- CLEANERS & DEGREASERS
- PIPE STORAGE COMPOUNDS
- RUST & CORROSION INHIBITORS
- THREAD LOCKING COMPOUNDS
- VALVE LUBRICANTS & SEALANTS
- TOOL JOINT & DRILL COLLAR COMPOUNDS

### PRODUCT DESCRIPTION

PM600 is a heavy-duty, all-purpose lubricant manufactured specifically for bearings and open gears. PM600 is tacky and has very high shock-absorbing abilities with a high melting point of +500°F (260°C). PM600 is a grease manufactured with exceptional adhesive and cohesive properties, allowing longer service intervals. PM600 forms a lubricating film that prevents metal-to-metal contact and reduces operating temperatures. It is water-resistant and protects against corrosion as it lubricates.

### BENEFITS

- Non-melting
- Film forming
- Excellent cohesive and adhesive properties
- High shock load
- Water resistant

### APPLICATION

PM600 is generally within the temperature range to lubricate wheel bearings, chassis, ball-joints, water pumps, fifth wheels, universal joints, slides, pillow block bearings, guide rails, cams, winches, or any other equipment requiring an extreme pressure lubricant. PM600 is used in many industries such as automotive, marine, aircraft, air conditioning, mining, construction, sugarcane mills, oil fields, cement plants, farms, chemical plants, and food plants.

### CONTAINER SIZE

- Cart Case (50 carts)
- 1 Gal (4 L)
- 5 Gal (19 L)
- Quarter Drum
- 55 Gal (208 L)

### RELATED PRODUCTS

- 627 Premium Valve Lubricant
- PM600M Premium Gear and Bearing with Moly
- PM800 Premium Bearing Lube
- PM800M Premium Bearing Lube with Moly
- PM900 Military Grease

### TYPICAL OBSERVATIONS

	PM600N000	PM600N00	PM600N0	PM600N1	PM600N2	PM600N3
Color	Red	Red	Red	Red	Red	Red
Texture	Tacky	Tacky	Tacky	Tacky	Tacky	Tacky
Penetration, ASTM D-217 @ 77°F (25°C)	445–475	400–430	355–385	310–340	265–295	220–250
Density, lb/gal @ 77°F (25°C)	7.40	7.42	7.44	7.46	7.47	7.50
Specific Gravity @ 77°F (25°C)	0.886	0.889	0.891	0.893	0.895	0.899
Flash Point, ASTM D-92	>400°F (>204°C)	>400°F (>204°C)	>400°F (>204°C)	>400°F (>204°C)	>400°F (>204°C)	>400°F (>204°C)
Dropping Point, ASTM D-2265	+500°F (+260°C)	+500°F (+260°C)	+500°F (+260°C)	+500°F (+260°C)	+500°F (+260°C)	+500°F (+260°C)
Water Washout, ASTM D-1264 @100°F (37°C)	6.0%	5.8%	5.8%	5.1%	4.8%	4.2%
Freezing Point	-17°F (-27°C)	-13°F (-25°C)	-4°F (-20°C)	-4°F (-20°C)	0°F (-17°C)	3°F (-16°C)
4-Ball EP Weld load, KgF (ASTM D-2596)	200 Pass 250 weld	200 Pass 250 weld	200 Pass 250 weld	200 Pass 250 weld	200 Pass 250 weld	200 Pass 250 weld
Evaporation Loss, ASTM D-972 @ 210°F (98°C)	1.30	1.30	1.28	1.20	1.15	1.00
Shelf Life (unopened container)	Two years	Two years	Two years	Two years	Two years	Two years



© 2012, BALMAR, LLC Made in U.S.A.  
**WARRANTY** Because the conditions of use and the supervision of application are beyond our control, we assume no liability for any product failure or other damage beyond the purchase price of the material furnished by us. No agent, representative, or employee of this Company is authorized to change this provision, which relates to all goods delivered, whether sold, delivered as samples, or otherwise. Each user should independently determine the suitability of this product based on their specific application.

Manufactured by  
**BALMAR, L.L.C.**

616 WEST PONT DES MOUTON ROAD | LAFAYETTE, LA 70507

Sales Locations:  
LAFAYETTE, LA | HOUSTON, TX | LONGVIEW, TX | MIDLAND, TX | OKLAHOMA CITY, OK

\*Registered trade name of Oil Center Research, Inc. 09/26/13  
The product information and specifications listed in this publication are constantly being updated to keep up with government regulations and technology changes. Please visit our web site, [www.oilcenter.com](http://www.oilcenter.com), or contact your Account Representative for the most current information relating to this product.